


NEW!
satin finish

PRECONSTRAINT

502 SATIN



502V2-2160C

See reverse for additional colors.


Serge Ferrari

PRECONTRAIN 502 SATIN

MAIN FEATURES

- Satin finish **NEW!**
- Dimensional stability
- Flexibility and strength
- Heat and weather protection
- High UV resistance
- Exceptional dirt resistance thanks to a PVDF topcoat on both sides
- Wide range of colors - 13 **NEW** colors!
- 10 year warranty

APPLICATIONS

- Awnings
- Canopies
- Shade sails
- Light structures
- Tents

TECHNICAL PROPERTIES

	Preconstraint 502 Satin	Standards
Yarn	1100 dtex PES HT	
Weight	16.7 oz/sqyd	EN ISO 2286-2
Roll width	70.9"	
Roll length	54.68 yds (50 lm)	
Tensile strength (warp/weft)	200/200 daN / 5 cm	EN ISO 1421
Tear strength (warp/weft)	20/20 daN	DIN 53.363
Adhesion	7/7 daN / 5 cm	EN ISO 2411
Flame retardancy	Method 1 /NFPA 701 • CSFM T19 • Class A/ASTM E84	
Quality management system		ISO 9001

Certifications, labels, warranties, recycling



The technical data above are averaged values with a +/- 5% tolerance.

The buyer of our products is fully responsible for their application and their transformation with regard to any possible third party. The buyer of our products is responsible for their implementation and installation according to the standards, workmanship and safety regulations in force in destination countries. For information on our contractual warranty, please refer to the relevant terms and conditions.

The values quoted above represent results of tests performed in compliance with common design practices and are provided for information only to enable customers to make the best use of our products. Our products are subject to changes based on technical advances and we reserve the right to modify their characteristics at any time. The buyer of our products is responsible for checking the validity of the above data.

→ Contact

SERGE FERRARI NORTH AMERICA
1460 SW 6th Court
Pompano Beach, FL. 33069
T: (954) 942-3600
marketing.us@sergeferrari.com

→ TEXYLOOP®

- The Serge Ferrari operational recycling chain
- Secondary raw materials of high intrinsic value compatible with multiple processes
- A quantified response to combat depletion of natural resources

www.texyloop.com



The colors and textures represented in this document are provided as a reference only. Whether viewed on screen or printed, they can not accurately match the real Preconstraint range colors and are therefore not contractual.

US | Preconstraint is a registered trademark of Serge Ferrari sas.
OCTOBER 2015/V1.0

Cover Photo: LEGOLAND, Orlando, Florida
Courtesy Awning Works, Clearwater, Florida